

**ECOMID® A J20 BK 2000/1**

PA66

Celanese

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>71</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>216</b>	°C	ISO 75-1/-2

[C]: CAMPUS

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<sup>[C]</sup> Density	<b>1080</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics****Delivery form**

Black

**Certifications**

Recycled Resin Content