

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2900	MPa	ISO 527
Yield stress	70	MPa	ISO 527
Strain at break	45	%	ISO 527
Flexural modulus, 23°C	2400	MPa	ISO 178
Izod notched impact strength, +23°C	5	kJ/m <sup>2</sup>	ISO 180/1A
Rockwell hardness	R 118	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	195	°C	ISO 75-1/-2
Vicat softening temperature, B	235	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Density	1140	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	265 - 285	°C	-
Mold temperature	70 - 120	°C	-

## Characteristics

### Processing

Injection Molding

### Regional Availability

North America, Europe, Asia Pacific