

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
Molding shrinkage, normal	1.2	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2900	MPa	ISO 527
Yield stress	60	MPa	ISO 527
Strain at break	25	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6.5	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	195	°C	ISO 75-1/-2
Vicat softening temperature, B	210	°C	ISO 306
Burning behav. at thickness h	V-2	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Comparative tracking index	350	-	IEC 60112
Other properties			
Density	1260	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	70 - 90	°C	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific

Special Characteristics

Flame retardant, High impact or impact modified