

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.018</b>	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Modulus	<b>3470</b>	MPa	ASTM D 638
Tensile Strength at Yield	<b>53.8</b>	MPa	ASTM D 638
Elongation at Break	<b>24</b>	%	ASTM D 638
Flexural Modulus	<b>2810</b>	MPa	ASTM D 790
Flexural Strength	<b>93.1</b>	MPa	ASTM D 790
Izod Impact notched, 1/4 in	<b>59</b>	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Density	<b>1520</b>	kg/m <sup>3</sup>	ASTM D 792

### Characteristics

#### Delivery form

Pellets, Black

#### Applications

Automotive

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa