

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	44.8	MPa	ASTM D 638
Elongation at Break	40	%	ASTM D 638
Flexural Modulus	1630	MPa	ASTM D 790
Flexural Strength	64.8	MPa	ASTM D 790
Izod Impact notched, 1/8 in	640	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	50	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Water Absorption, Equilibrium	1.2	%	ASTM D 570
Density	1110	kg/m ³	ASTM D 792

Characteristics

Delivery form
Pellets, Black

Certifications
Recycled Resin Content

Additives
Lubricants

Applications
General Purpose

Special Characteristics
Heat stabilized or stable to heat

Regional Availability
North America