

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.7 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	2.0 / *	%	ISO 294-4, 2577
Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	2350 / 1250	MPa	ISO 527
Stress at break	55 / 35	MPa	ISO 527
Strain at break	>50 / 40	%	ISO 527
Flexural modulus, 23°C	2100 / -	MPa	ISO 178
Charpy notched impact strength, +23°C	28 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	25 / -	kJ/m ²	ISO 180/1A
Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB / *	class	IEC 60695-11-10
	1.6 / *	mm	-
Other properties	dry / cond	Unit	Test Standard
Density	1090 / -	kg/m ³	ISO 1183
Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	260	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Additives

Lubricants

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

Europe