

EPLON 66 IMP NC Q1A501

PA66

Epsan Plastik San. Tic. A.Ş

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
Molding shrinkage, normal	2.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2250	MPa	ISO 527
Stress at break	57	MPa	ISO 527
Strain at break	15	%	ISO 527
Flexural modulus, 23°C	2000	MPa	ISO 178
Charpy notched impact strength, +23°C	10.5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	250	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB	class	IEC 60695-11-10
	1.6	mm	-
Other properties			
Density	1090	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	280	°C	-

Characteristics**Processing**

Injection Molding

Delivery form

Natural Color

Additives

Lubricants

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

Europe