

FORMPOLY N66GP30FR

PA66

Formulated Polymers Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.009	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	70	MPa	ASTM D 638
Elongation at Break	4	%	ASTM D 638
Flexural Modulus	2700	MPa	ASTM D 790
Flexural Strength	110	MPa	ASTM D 790
Izod Impact notched, 1/8 in	39.2	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
DTUL @ 66 psi	145	°C	ASTM D 648
DTUL @ 264 psi	75	°C	ASTM D 648

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	1E14	Ohm	ASTM D 257
Volume Resistivity	1E15	Ohm*cm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	1280	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Pellets

Special Characteristics

Flame retardant

Features

Low Odor, Low Warpage

Chemical Resistance

Environmental Stress Crack Resistance

Applications

Electrical and Electronical

Regional Availability

Asia Pacific