

FORMPOLY N66MS30

PA66

Formulated Polymers Limited

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0165	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Strength	75	MPa	ASTM D 638
Elongation at Break	30	%	ASTM D 638
Flexural Modulus	2800	MPa	ASTM D 790
Flexural Strength	110	MPa	ASTM D 790
Izod Impact notched, 1/8 in	49.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	155	°C	ASTM D 648
DTUL @ 264 psi	70	°C	ASTM D 648
Electrical properties			
ASTM Data			
Surface Resistivity	1E14	Ohm	ASTM D 257
Volume Resistivity	1E15	Ohm*cm	ASTM D 257
Other properties			
Density	1140	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets

Features

Low Odor

Additives

Lubricants

Regional Availability

Asia Pacific