

| Processing/Physical Characteristics | dry / cond | Unit | Test Standard |
|--|-------------------|------------------------|----------------------|
| ISO Data | | | |
| ^[C] Melt volume-flow rate, MVR | 235 / * | cm ³ /10min | ISO 1133 |
| Temperature | 275 / * | °C | - |
| Load | 5 / * | kg | - |

[C]: CAMPUS

| Mechanical properties | dry / cond | Unit | Test Standard |
|--|-------------------|-------------------|----------------------|
| ISO Data | | | |
| ^[C] Tensile Modulus | 3500 / - | MPa | ISO 527 |
| ^[C] Charpy impact strength, +23°C | 100 / - | kJ/m ² | ISO 179/1eU |
| ^[C] Charpy notched impact strength, +23°C | 3 / - | kJ/m ² | ISO 179/1eA |

[C]: CAMPUS

| Other properties | dry / cond | Unit | Test Standard |
|-------------------------|-------------------|-------------------|----------------------|
| ^[C] Density | - / 1160 | kg/m ³ | ISO 1183 |

[C]: CAMPUS

Characteristics

Special Characteristics

Flame retardant

Regional Availability

Asia Pacific