

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.6	%	ISO 294-4, 2577
Molding shrinkage, normal	1.9	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2850	MPa	ISO 527
Yield stress	80	MPa	ISO 527
Yield strain	3.8	%	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	2900	MPa	ISO 178
Flexural strength	92	MPa	ISO 178
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4.7	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.1	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	4.8	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	207	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Humidity absorption	2.6	%	Sim. to ISO 62
Density	1140	kg/m ³	ISO 1183

Material specific properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	155 ^[1]	cm ³ /g	ISO 307, 1157, 1628

1: VN at 0.5% in sulfuric acid, nominal

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	6 - 10	h	-
Processing humidity	≤0.2	%	-
Melt temperature	280 - 295	°C	-
Mold temperature	50 - 90	°C	-
Zone 1	250 - 270	°C	-
Zone 2	270 - 290	°C	-
Zone 3	270 - 290	°C	-
Nozzle temperature	270 - 295	°C	-
Screw speed	75 - 180	rpm	-
Back pressure	0.2 - 1	MPa	-

Characteristics

Processing
Injection Molding, Other Extrusion

Features
Color Stability

Applications
General Purpose

Regional Availability
North America, Europe, Asia Pacific, South and Central America

Certifications

RoHS compliant