

KEPAMID® 2300SF

PA66

Korea Engineering Plastics Co. Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.1	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Strength	70	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	2500	MPa	ISO 178
Charpy notched impact strength, +23°C	15	kJ/m ²	ISO 179/1eA
Rockwell hardness	R115	-	ISO 2039-2
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Relative permittivity, 1MHz	3.2	-	IEC 62631-2-1
Other properties			
Humidity absorption	1.2	%	Sim. to ISO 62
Density	1110	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	80 - 90	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.05	%	-
Mold temperature	70 - 90	°C	-
Feed temperature	60 - 80	°C	-
Zone 1	270	°C	-
Zone 2	280	°C	-
Zone 3	280	°C	-
Nozzle temperature	285	°C	-
Screw speed	80 - 120	rpm	-
Back pressure	0.5 - 1	MPa	-

Characteristics**Processing**

Injection Molding

Applications

Automotive, Electrical and Electronical

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America, Europe, Asia Pacific