

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.0195</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>82</b>	MPa	ASTM D 638
Flexural Modulus	<b>2845</b>	MPa	ASTM D 790
Flexural Strength	<b>118</b>	MPa	ASTM D 790
Rockwell Hardness	<b>R 120</b>	-	ASTM D 785
Izod Impact notched, 1/8 in	<b>68</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>0.8</b>	mm	-
Coefficient of Thermal Expansion, MD	<b>70</b>	E-6/K	ASTM D 696
DTUL @ 66 psi	<b>225</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>70</b>	°C	ASTM D 648
Melting Temperature	<b>255</b>	°C	ASTM D 3418
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>20</b>	kV/mm	ASTM D 149
Dielectric Constant, 1 MHz	<b>3.3</b>	-	ASTM D 150
Arc Resistance	<b>128</b>	s	ASTM D 495
<b>Other properties</b>			
Water Absorption, 24hr	<b>1.3</b>	%	ASTM D 570
Density	<b>1140</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Special Characteristics

Heat stabilized or stable to heat

### Regional Availability

North America, Asia Pacific