

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.2	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	2800	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	2.5	%	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	10	%	ISO 527
Charpy notched impact strength, +23°C	N	kJ/m ²	ISO 179/1eA
Tensile notched impact strength, +23°C	7	kJ/m ²	ISO 8256/1
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	70	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	170	°C	ISO 75-1/-2
Vicat softening temperature, B	180	°C	ISO 306
Coeff. of linear therm. expansion, parallel	110	E-6/K	ISO 11359-1/-2
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	2	mm	-
Glow Wire Ignition Temperature (GWIT)	775	°C	IEC 60695-2-13
GWIT - thickness tested (1)	1	mm	-
Glow Wire Ignition Temperature (GWIT)	775	°C	IEC 60695-2-13
GWIT - thickness tested (2)	2	mm	-
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.75	mm	-
Limiting Oxygen Index	34	%	ASTM D 2863
Electrical properties			
ISO Data			
Comparative tracking index	250	-	IEC 60112
ASTM Data			
Surface Resistivity	1E12	Ohm	ASTM D 257
Other properties			
Density	1350	kg/m ³	ISO 1183
Processing Recommendation Injection Molding			
Pre-drying - Temperature	90 - 100	°C	-
Pre-drying - Time	3	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	70 - 90	°C	-

Characteristics

Processing

Injection Molding

Additives

Flame retarding agent

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe