

Product Texts

LNP LUBRILOY RX05498 compound is based on Nylon 6/6 resin containing proprietary lubricant. Added features of this grade include: High Impact, Wear Resistant.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	2.5	%	ISO 294-4, 2577
Molding shrinkage, normal	2.5	%	ISO 294-4, 2577
ASTM Data			
Mold Shrinkage, MD	2.5	mm/mm	ASTM D 955
Mold Shrinkage, TD	2.5	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2160	MPa	ISO 527
Yield stress	55	MPa	ISO 527
Yield strain	16	%	ISO 527
Stress at break	54	MPa	ISO 527
Strain at break	50	%	ISO 527
Flexural modulus	2000	MPa	ISO 178
Flexural strength	74	MPa	ISO 178
Izod impact strength, +23°C, 4mm	137	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	19	kJ/m ²	ISO 180/1A
ASTM Data			
Tensile Modulus	2220	MPa	ASTM D 638
Tensile Strength at Yield	59	MPa	ASTM D 638
Tensile Strength at Break	53	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Elongation at Break	31	%	ASTM D 638
Flexural Modulus	2080	MPa	ASTM D 790
Flexural Strength	80	MPa	ASTM D 790
Izod Impact notched, 1/8 in	427	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	67	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	188	°C	ISO 75-1/-2
ASTM Data			
DTUL @ 66 psi	206	°C	ASTM D 648
DTUL @ 264 psi	63	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	1.12	%	Sim. to ISO 62
Density	1100	kg/m ³	ISO 1183
Water Absorption, 24hr	0.7	%	ASTM D 570
Density	1100	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.25	%	-
Melt temperature	280 - 305	°C	-
Mold temperature	95 - 110	°C	-
Zone 1	265 - 275	°C	-
Zone 2	280 - 295	°C	-
Zone 3	295 - 305	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific