

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	65	g/10min	ASTM D 1238
Temperature	275	°C	-
Load	5	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	50	MPa	ASTM D 638
Elongation at Break	71	%	ASTM D 638
Flexural Modulus	1751	MPa	ASTM D 790
Flexural Strength	83	MPa	ASTM D 790
Izod Impact notched, 1/8 in	908	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	260	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	1080	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

High impact or impact modified

Regional Availability

Europe, Asia Pacific

Certifications

RoHS compliant