

NEVIMID 66 E400

PA66

Nevicolor S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.8	%	ISO 294-4, 2577
Molding shrinkage, normal	1.8	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Tensile Modulus	1900	MPa	ISO 527
Yield stress	50	MPa	ISO 527
Yield strain	5	%	ISO 527
Stress at break	40	MPa	ISO 527
Strain at break	>50	%	ISO 527
Flexural modulus, 23°C	1600	MPa	ISO 178
Izod impact strength, +23°C	N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	85	kJ/m ²	ISO 180/1A
Izod notched impact strength	50	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	150	°C	ISO 75-1/-2
Vicat softening temperature, A	245	°C	ISO 306
Vicat softening temperature, B	210	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
Other properties			
Humidity absorption	0.8	%	Sim. to ISO 62
Density	1060	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

High impact or impact modified

Regional Availability

Europe