

**NEVIMID 66 SC**

PA66

Nevicolor S.p.A.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	1.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.3	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	2700	MPa	ISO 527
Yield stress	70	MPa	ISO 527
Yield strain	4	%	ISO 527
Stress at break	50	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178
Izod impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	4	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-20	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	180	°C	ISO 75-1/-2
Vicat softening temperature, A	255	°C	ISO 306
Vicat softening temperature, B	220	°C	ISO 306
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.2	mm	-
<b>Other properties</b>			
Humidity absorption	1.2	%	Sim. to ISO 62
Density	1120	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

High impact or impact modified

**Regional Availability**

Europe