

| Mechanical properties | Value | Unit | Test Standard |
|------------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Tensile Modulus | 2372 | MPa | ASTM D 638 |
| Tensile Strength | 60.5 | MPa | ASTM D 638 |
| Flexural Modulus | 2103 | MPa | ASTM D 790 |
| Izod Impact notched, 1/8 in | 160 | J/m | ASTM D 256 |

| Thermal properties | Value | Unit | Test Standard |
|---------------------------|--------------|-------------|----------------------|
| ASTM Data | | | |
| Melting Temperature | 252 | °C | ASTM D 3418 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1080 | kg/m ³ | ASTM D 792 |

| Processing Recommendation Injection Molding | Value | Unit | Test Standard |
|--|------------------|-------------|----------------------|
| Pre-drying - Temperature | 65 - 82 | °C | - |
| Pre-drying - Time | 2 - 4 | h | - |
| Processing humidity | ≤0.2 | % | - |
| Melt temperature | 282 - 304 | °C | - |
| Mold temperature | 49 - 93 | °C | - |
| Zone 1 | 260 - 282 | °C | - |
| Zone 2 | 271 - 293 | °C | - |
| Zone 3 | 282 - 304 | °C | - |
| Nozzle temperature | 279 - 301 | °C | - |
| Injection pressure | 7 - 15 | MPa | - |
| Back pressure | 0 - 50 | MPa | - |
| Holding pressure | 5 - 12 | MPa | - |
| Maximum residence time | 6 | min | - |

Characteristics

Processing

Injection Molding

Delivery form

Black

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America