

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	73	MPa	ISO 527
Yield strain	7	%	ISO 527
Flexural modulus, 23°C	2490	MPa	ISO 178
Flexural strength	102	MPa	ISO 178
Izod notched impact strength, +23°C	7.5	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3

Other properties	Value	Unit	Test Standard
Density	1120	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	90	°C	-
Pre-drying - Time	4	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	80 - 90	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Black

Special Characteristics

High impact or impact modified, Heat stabilized or stable to heat

Regional Availability

North America, Europe, South and Central America