

**POLIMID A EM1**

PA66

Poliblend S.p.a.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Molding shrinkage, parallel	1.8	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	2400	MPa	ISO 527
Yield stress	65	MPa	ISO 527
Yield strain	6.5	%	ISO 527
Strain at break	>50	%	ISO 527
Izod impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	12	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	195	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	1E12	Ohm*m	IEC 62631-3-1
Comparative tracking index	600	-	IEC 60112
<b>Other properties</b>			
Density	1110	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Regional Availability**

Europe