

Product Texts

Starflam 366 BK13 (formerly Vydyne® ECO366 BK13) is a non-halogenated, unreinforced, flame-retardant PA66 compound designed with high comparative tracking index (CTI) and low corrosion for improved electrical contact performance. It has superior flow properties to assist in filling thin-walled, intricate parts with reduced warpage and reduced cycle time. It is lubricated for machine feed and easy mold release. It is f1 rated in black.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	0.9 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.2 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Charpy impact strength, +23°C	75 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	78 / -	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	3.4 / -	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	3.7 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	265 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	75 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	240 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
^[C] Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	0.4 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Oxygen index	35 / *	%	ISO 4589-1/-2

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E8 / -	Ohm*m	IEC 62631-3-1
^[C] Electric strength	17 / -	kV/mm	IEC 60243-1
^[C] Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Water absorption	0.8 / *	%	Sim. to ISO 62
^[C] Humidity absorption	2.3 / *	%	Sim. to ISO 62
^[C] Density	1170 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Black

Additives

Lubricants

Special Characteristics

Flame retardant, Halogen-free, Heat stabilized or stable to heat

Features

Low Warpage

Regional Availability

North America, Europe, Asia Pacific