

**Taromid A 280 R2**

PA66

Taro Plast S.p.A.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>8</b>	g/10min	ISO 1133
Temperature	<b>280</b>	°C	-
Load	<b>1</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	<b>62</b>	MPa	ISO 527
Strain at break	<b>&gt;50</b>	%	ISO 527
Flexural modulus, 23°C	<b>2100</b>	MPa	ISO 178
<b>ASTM Data</b>			
Izod Impact notched, 1/8 in	<b>100</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>256</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>70</b>	°C	ISO 75-1/-2
Vicat softening temperature, B	<b>215</b>	°C	ISO 306
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>0.97</b>	mm	-
Limiting Oxygen Index	<b>23</b>	%	ASTM D 2863
<b>Electrical properties</b>			
<b>ISO Data</b>			
Comparative tracking index	<b>550</b>	-	IEC 60112
<b>Other properties</b>			
Water absorption	<b>5.5</b>	%	Sim. to ISO 62
Density	<b>1090</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Additives**

Release agent

**Special Characteristics**

High impact or impact modified, U.V. stabilized or stable to weather

**Features**

Low Odor

**Chemical Resistance**

General Chemical Resistance, Solvent Resistance, Oil Resistance

**Applications**

Automotive, Electrical and Electronical

**Regional Availability**

Europe