

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2950	MPa	ISO 527
Tensile Strength	80	MPa	ISO 527
Strain at break	85	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	72	°C	ISO 11357-1/-2

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ISO 1183
Bulk density	600	kg/m ³	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.1	%	-
Melt temperature	260 - 300	°C	-
Mold temperature	70 - 110	°C	-
Zone 1	250 - 300	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Brown

Regional Availability

North America, Europe, Asia Pacific, South and Central America