

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	35	cm ³ /10min	ISO 1133
Temperature	275	°C	-
Load	5	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1900	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Yield strain	11.5	%	ISO 527
Flexural modulus, 23°C	1700	MPa	ISO 178
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	260	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	130	°C	ISO 75-1/-2
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Comparative tracking index	550	-	IEC 60112
Other properties			
Water absorption	8.2	%	Sim. to ISO 62
Humidity absorption	2.4	%	Sim. to ISO 62
Density	1060	kg/m ³	ISO 1183

Characteristics

Special Characteristics

High impact or impact modified

Regional Availability

North America, Europe