

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.6 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.5 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3300 / 1300	MPa	ISO 527
^[C] Stress at 50% strain	* / 50	MPa	ISO 527
^[C] Stress at break	55 / *	MPa	ISO 527
^[C] Strain at break	20 / >50	%	ISO 527
Flexural modulus, 23°C	3000 / 1300	MPa	ISO 178
Flexural strength	120 / 70	MPa	ISO 178
^[C] Charpy notched impact strength, +23°C	4.5 / 10	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	263 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	82 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	200 / *	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	* / 1E15	Ohm	IEC 62631-3-2
^[C] Electric strength	22 / -	kV/mm	IEC 60243-1
^[C] Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
^[C] Density	1140 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Delivery form

Black

Special Characteristics

Heat stabilized or stable to heat

Applications

General Purpose