

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	1.5 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	2700 / -	MPa	ISO 527
<sup>[C]</sup> Yield stress	54 / -	MPa	ISO 527
<sup>[C]</sup> Yield strain	5 / -	%	ISO 527
Flexural modulus, 23°C	2900 / -	MPa	ISO 178
Flexural strength	100 / -	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	55 / -	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	4 / -	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	257 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	73 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	204 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Electric strength	39 / -	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	400 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Density	1350 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Black

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Applications**

Electrical and Electronical