

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3500	MPa	ISO 527
Yield stress	85	MPa	ISO 527
Izod impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	262	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	80	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2

Other properties	Value	Unit	Test Standard
Humidity absorption	2.6	%	Sim. to ISO 62
Density	1150	kg/m <sup>3</sup>	ISO 1183
Moisture Content	0.2	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	270 - 290	°C	-
Mold temperature	50 - 90	°C	-
Feed temperature	60 - 80	°C	-
Holding pressure	50 - 100	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

Europe

**Delivery form**

Natural Color