

Product Texts

Vydyne 20NSP BLK is a general-purpose, highly nucleated, lubricated PA66 resin with a further enhanced crystallization temperature. Designed to crystallize rapidly in order to reduce cycle times and increase productivity through faster part set-up.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
^[C] Molding shrinkage, parallel	1.4 / *	%	ISO 294-4, 2577
^[C] Molding shrinkage, normal	1.6 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	3800 / 2500	MPa	ISO 527
^[C] Yield stress	95 / 60	MPa	ISO 527
^[C] Yield strain	5 / 15	%	ISO 527
Flexural modulus, 23°C	3200 / 1300	MPa	ISO 178
Flexural strength	100 / 35	MPa	ISO 178
^[C] Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy impact strength, -30°C	N / N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	6 / 15	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	5 / 5	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	6 / 15	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	5 / 5	kJ/m ²	ISO 180/1A
	-30	°C	-

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
^[C] Temp. of deflection under load, 1.80 MPa	90 / *	°C	ISO 75-1/-2
^[C] Temp. of deflection under load, 0.45 MPa	230 / *	°C	ISO 75-1/-2
^[C] Coeff. of linear therm. expansion, parallel	100 / *	E-6/K	ISO 11359-1/-2
^[C] Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn. Thickness tested	V-2 / *	class	IEC 60695-11-10
	1.5 / *	mm	-
^[C] Burning Behav. at thickness h Thickness tested	V-2 / *	class	IEC 60695-11-10
	0.4 / *	mm	-
Yellow Card available	yes / *	-	-
^[C] Oxygen index	26 / *	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	0.4	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (2)	0.71	mm	-
Glow Wire Flammability Index (GWFI)	960	°C	IEC 60695-2-12
GWFI - thickness tested (3)	1.5	mm	-
Glow Wire Ignition Temperature (GWIT)	825	°C	IEC 60695-2-13
GWIT - thickness tested (1)	0.4	mm	-
Glow Wire Ignition Temperature (GWIT)	850	°C	IEC 60695-2-13
GWIT - thickness tested (2)	0.71	mm	-
Glow Wire Ignition Temperature (GWIT)	850	°C	IEC 60695-2-13
GWIT - thickness tested (3)	1.5	mm	-
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.4	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	1E11 / -	Ohm*m	IEC 62631-3-1

[C] Electric strength	26 / -	kV/mm	IEC 60243-1
[C] Comparative tracking index	600 / -	-	IEC 60112
ASTM Data			
Arc Resistance	150 / -	s	ASTM D 495

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Water absorption	1.2 / *	%	Sim. to ISO 62
[C] Humidity absorption	2.4 / *	%	Sim. to ISO 62
[C] Density	1140 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	70	°C	-
Pre-drying - Time	1 - 3	h	-
Melt temperature	285 - 300	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	260 - 280	°C	-
Zone 2	270 - 285	°C	-
Zone 3	280 - 290	°C	-
Nozzle temperature	280 - 300	°C	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Black

Additives

Lubricants, Release agent

Features

High Crystallinity, Nucleated

Chemical Resistance

General Chemical Resistance

Applications

Electrical and Electronical, General Purpose

Regional Availability

North America, Europe, Asia Pacific