

**Product Texts**

Vydyne 47 NT is a general-purpose, medium impact-modified PA66 resin. 47 NT is recognized for all the processing and property advantages inherent to PA66 with the addition of improved impact strength. This resin offers a well balanced combination of engineering properties characterized by high melt point, good surface lubricity, abrasion resistance and resistance to many chemicals, machine and motor oils, solvents and gasoline. 47 NT is designed to meet the critical low-temperature impact requirements called out in many automotive specifications.

<b>Processing/Physical Characteristics</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	<b>1.8 / *</b>	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	<b>1.6 / *</b>	%	ISO 294-4, 2577

[C]: CAMPUS

<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>2800 / 1700</b>	MPa	ISO 527
Yield stress	<b>60 / 45</b>	MPa	ISO 527
Stress at break	<b>52 / 40</b>	MPa	ISO 527
Strain at break	<b>22 / 60</b>	%	ISO 527
Flexural modulus, 23°C	<b>2300 / 780</b>	MPa	ISO 178
Flexural strength	<b>70 / 24</b>	MPa	ISO 178
<sup>[C]</sup> Charpy impact strength, +23°C	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	<b>19 / 62</b>	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	<b>17 / 24</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	<b>18 / 44</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>12 / 18</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-40</b>	°C	-

[C]: CAMPUS

<b>Thermal properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	<b>260 / *</b>	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	<b>63 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	<b>185 / *</b>	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	<b>111 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	<b>136 / *</b>	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>1.5 / *</b>	mm	-
<sup>[C]</sup> Burning Behav. at thickness h	<b>HB / *</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / *</b>	mm	-
Glow Wire Flammability Index (GWFI)	<b>750</b>	°C	IEC 60695-2-12
GWFI - thickness tested (1)	<b>0.75</b>	mm	-
Glow Wire Flammability Index (GWFI)	<b>775</b>	°C	IEC 60695-2-12
GWFI - thickness tested (2)	<b>1.5</b>	mm	-
Glow Wire Flammability Index (GWFI)	<b>725</b>	°C	IEC 60695-2-12
GWFI - thickness tested (3)	<b>3</b>	mm	-
Glow Wire Ignition Temperature (GWIT)	<b>775</b>	°C	IEC 60695-2-13
GWIT - thickness tested (1)	<b>0.75</b>	mm	-
Glow Wire Ignition Temperature (GWIT)	<b>800</b>	°C	IEC 60695-2-13
GWIT - thickness tested (2)	<b>1.5</b>	mm	-
Glow Wire Ignition Temperature (GWIT)	<b>750</b>	°C	IEC 60695-2-13
GWIT - thickness tested (3)	<b>3</b>	mm	-
<b>ASTM Data</b>			
UL 94 Flame rating	<b>HB</b>	-	UL 94
Thickness tested	<b>0.75</b>	mm	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Volume resistivity	1E10 / -	Ohm*m	IEC 62631-3-1
<sup>[C]</sup> Electric strength	24 / -	kV/mm	IEC 60243-1
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112
<b>ASTM Data</b>			
Arc Resistance	150 / -	s	ASTM D 495

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	1.2 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	2.3 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1100 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	4	h	-
Melt temperature	285 - 305	°C	-
Mold temperature	65 - 95	°C	-
Zone 1	280 - 310	°C	-
Zone 2	280 - 310	°C	-
Zone 3	280 - 310	°C	-
Nozzle temperature	280 - 310	°C	-

**Characteristics**

**Processing**

Injection Molding

**Delivery form**

Pellets, Natural Color

**Additives**

Lubricants

**Special Characteristics**

High impact or impact modified

**Chemical Resistance**

General Chemical Resistance, Solvent Resistance, Oil Resistance

**Applications**

Automotive, Electrical and Electronical, General Purpose

**Regional Availability**

North America, Europe, Asia Pacific