

**Product Texts**

Vydyne 65A NT0751 is a medium-viscosity, heat-stabilized PA66 resin suitable for injection-molding, extrusion and compounding applications. It is available in natural color only. 65A NT0751 resin offers high strength, rigidity and toughness over a broad range of demanding applications, and good fluid resistance to a wide variety of chemicals, solvents and oils.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	2.0 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.8 / *	%	ISO 294-4, 2577

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	3100 / 1800	MPa	ISO 527
<sup>[C]</sup> Yield stress	85 / 50	MPa	ISO 527
<sup>[C]</sup> Yield strain	5.5 / 21	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy impact strength, -30°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
<sup>[C]</sup> Charpy notched impact strength, +23°C	5 / 35	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	6 / 7	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	260 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	200 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, parallel	100 / *	E-6/K	ISO 11359-1/-2
<sup>[C]</sup> Coeff. of linear therm. expansion, normal	100 / *	E-6/K	ISO 11359-1/-2

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Humidity absorption	2.3 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1140 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

**Characteristics**

**Processing**

Injection Molding, Other Extrusion

**Chemical Resistance**

General Chemical Resistance, Solvent Resistance, Oil Resistance

**Delivery form**

Pellets, Natural Color

**Regional Availability**

North America, Europe, Asia Pacific

**Special Characteristics**

Heat stabilized or stable to heat