

Product Texts

is an unreinforced PA66 for injection molded applications.

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
[C] Tensile Modulus	3000 / -	MPa	ISO 527
[C] Charpy impact strength, +23°C	100 / -	kJ/m ²	ISO 179/1eU
[C] Charpy notched impact strength, +23°C	5 / -	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
[C] Humidity absorption	2 / *	%	Sim. to ISO 62
[C] Density	1140 / -	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

Heat stabilized or stable to heat

Delivery form

Pellets

Regional Availability

North America, Europe

Additives

Release agent