

## Product Texts

Common features of Zytel® nylon resin include mechanical and physical properties such as high mechanical strength, excellent balance of stiffness and toughness, good high temperature performance, good electrical and flammability properties, good abrasion and chemical resistance. In addition, Zytel® nylon resins are available in different modified and reinforced grades to create a wide range of products with tailored properties for specific processes and end-uses. Zytel® nylon resin, including most flame retardant grades, offer the ability to be coloured.

The good melt stability of Zytel® nylon resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-31 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Zytel® nylon resin typically is used in demanding applications in the automotive, furniture, domestic appliances, sporting goods and construction industry.

## Zytel® 103HSL BKB080 is a heat stabilized, lubricated polyamide 66 resin for injection molding.

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Molding shrinkage, parallel	1.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Molding shrinkage, normal	1.3 / *	%	ISO 294-4, 2577
<sup>[C]</sup> Ejection temperature	190	°C	-

[C]: CAMPUS

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	3100 / 1400	MPa	ISO 527
<sup>[C]</sup> Yield stress	85 / 55	MPa	ISO 527
<sup>[C]</sup> Yield strain	4.3 / 25	%	ISO 527
<sup>[C]</sup> Nominal strain at break	20 / >50	%	ISO 527
<sup>[C]</sup> Tensile creep modulus, 1h	* / 1200	MPa	ISO 899-1
<sup>[C]</sup> Tensile creep modulus, 1000h	* / 650	MPa	ISO 899-1
<sup>[C]</sup> Charpy notched impact strength, +23°C	5.5 / 12	kJ/m <sup>2</sup>	ISO 179/1eA
<sup>[C]</sup> Charpy notched impact strength, -30°C	3 / 3	kJ/m <sup>2</sup>	ISO 179/1eA

[C]: CAMPUS

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Melting temperature, 10°C/min	262 / *	°C	ISO 11357-1/-3
<sup>[C]</sup> Glass transition temperature, 10°C/min	60 / *	°C	ISO 11357-1/-2
<sup>[C]</sup> Temp. of deflection under load, 1.80 MPa	70 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Temp. of deflection under load, 0.45 MPa	200 / *	°C	ISO 75-1/-2
<sup>[C]</sup> Burning Behav. at 1.5 mm nom. thickn.	V-2 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	-
Yellow Card available	yes / *	-	-
<sup>[C]</sup> Burning Behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.7 / *	mm	-
Yellow Card available	yes / *	-	-

[C]: CAMPUS

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Comparative tracking index	600 / -	-	IEC 60112

[C]: CAMPUS

Other properties	dry / cond	Unit	Test Standard
<sup>[C]</sup> Water absorption	8.5 / *	%	Sim. to ISO 62
<sup>[C]</sup> Humidity absorption	2.6 / *	%	Sim. to ISO 62
<sup>[C]</sup> Density	1140 / -	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

Material specific properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Viscosity number	150 / *	cm <sup>3</sup> /g	ISO 307, 1157, 1628
<small>[C]: CAMPUS</small>			

**Characteristics****Processing**

Injection Molding, Other Extrusion, Coating

**Special Characteristics**

Heat stabilized or stable to heat

**Delivery form**

Black

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America

**Additives**

Lubricants