4MID 9B20400

PA6 4Plas

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	**2800**	MPa	ISO 527
Stress at break	**75**	MPa	ISO 527
Strain at break	**35**	%	ISO 527
Izod notched impact strength, +23°C	**6**	kJ/m²	ISO 180/1A
Izod notched impact strength	**5**	kJ/m²	ISO 180/1A
Temperature	**-30**	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	**223**	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	**60**	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	**175**	°C	ISO 75-1/-2
Vicat softening temperature, B	**170**	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	**HB**	class	IEC 60695-11-10
Thickness tested	**1.6**	mm	-
Burning behav. at thickness h	**HB**	class	IEC 60695-11-10
Thickness tested	**3.2**	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	**1E13**	Ohm*m	IEC 62631-3-1
Surface resistivity	**1E13**	Ohm	IEC 62631-3-2
Comparative tracking index	**600**	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	**1130**	kg/m³	ISO 1183
Moisture Content	**0.2**	%	-

Characteristics

Special Characteristics	Regional Availability
U.V. stabilized or stable to weather	Europe

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.