

4MID 9B24200

PA6

4Plas

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2600	MPa	ISO 527
Stress at break	75	MPa	ISO 527
Strain at break	35	%	ISO 527
Izod notched impact strength, +23°C	11	kJ/m ²	ISO 180/1A
Izod notched impact strength Temperature	9 -30	kJ/m ² °C	ISO 180/1A -
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	223	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	160	°C	ISO 75-1/-2
Vicat softening temperature, B	170	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn. Thickness tested	HB 1.6	class mm	IEC 60695-11-10 -
Electrical properties			
ISO Data			
Comparative tracking index	600	-	IEC 60112
Other properties			
Density	1120	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Europe