

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	220	°C	ASTM D 3418
Other properties			
Moisture Content	0.1	%	-
Other Standards^{S1}			
Density	1130	kg/m ³	ASTM D 1505

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics

Delivery form

Pellets

Applications

Monofilament, Multifilament

Features

Homopolymer

Regional Availability

North America

Certifications

Recycled Resin Content