AKROMID® B3 1 FR grey (8051)

PA6 Akro-Plastic GmbH

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	**1.0 / ***	%	ISO 294-4, 2577
Molding shrinkage, normal	**1.1 / ***	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	**3600 / -**	MPa	ISO 527
Yield stress	**75 / -**	MPa	ISO 527
Charpy notched impact strength, +23°C	**4 / -**	kJ/m²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	**220 / ***	°C	ISO 11357-1/-3
Burning behav. at 1.5 mm nom. thickn.	**V-0 / ***	class	IEC 60695-11-10
Thickness tested	**1.6 / ***	mm	-
Yellow Card available	**yes / ***	-	-
Burning behav. at thickness h	**V-0 / ***	class	IEC 60695-11-10
Thickness tested	**0.4 / ***	mm	-
Yellow Card available	**yes / ***	-	-
Oxygen index	**32 / ***	%	ISO 4589-1/-2
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
GWFI - thickness tested (1)	**0.4**	mm	-
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
GWFI - thickness tested (2)	**0.8**	mm	-
Glow Wire Flammability Index (GWFI)	**960**	°C	IEC 60695-2-12
GWFI - thickness tested (3)	**1.6**	mm	-
Glow Wire Ignition Temperature (GWIT)	**775**	°C	IEC 60695-2-13
GWIT - thickness tested (1)	**0.4**	mm	-
Glow Wire Ignition Temperature (GWIT)	**750**	°C	IEC 60695-2-13
GWIT - thickness tested (2)	**0.8**	mm	-
Glow Wire Ignition Temperature (GWIT)	**750**	°C	IEC 60695-2-13
GWIT - thickness tested (3)	**1.6**	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Comparative tracking index	**600 / -**	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Density	**1190 / -**	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	**270**	°C	-
Mold temperature	**80**	°C	-
Injection pressure	**75**	MPa	-

Characteristics

Processing
Injection Molding

Applications
Electrical and Electronical

Special Characteristics
Flame retardant, Halogen-free, Heat stabilized or stable to heat

Regional Availability
Europe, Asia Pacific

Certifications
RoHS compliant

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.