

RTP 1000 TFE 10 Z

(PBT+PTFE)

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.019	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	2758	MPa	ASTM D 638
Tensile Strength	51.7	MPa	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Flexural Strength	82.7	MPa	ASTM D 790
Izod Impact notched, 1/8 in	58.7	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	HB	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	54.4	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1370	kg/m ³	ASTM D 792
Moisture Content	0.03	%	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	121	°C	-
Pre-drying - Time	4	h	-
Melt temperature	238 - 271	°C	-
Mold temperature	79.4 - 107	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Additives

Lubricants

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, Europe, Asia Pacific