

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>1.4</b>	mm/mm	ASTM D 955
Mold Shrinkage, TD	<b>2.2</b>	mm/mm	ASTM D 955

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Modulus	<b>4500</b>	MPa	ASTM D 638
Tensile Strength at Break	<b>57</b>	MPa	ASTM D 638
Elongation at Break	<b>2.9</b>	%	ASTM D 638
Flexural Modulus	<b>4390</b>	MPa	ASTM D 790
Flexural Strength	<b>103</b>	MPa	ASTM D 790

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
DTUL @ 264 psi	<b>180</b>	°C	ASTM D 648

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1420</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Regional Availability

Asia Pacific