

Alphalon® 25

PA6

Grupa Azoty S.A.

Product Texts

Alphalon® 25 is a bright polyamide 6 grade of low viscosity that is suited for the production of compounds.

| Thermal properties | Value | Unit | Test Standard |
|-------------------------------|--------------|-------------|----------------------|
| ISO Data | | | |
| Melting temperature, 10°C/min | 220 | °C | ISO 11357-1/-3 |

| Other properties | Value | Unit | Test Standard |
|-------------------------|--------------|-------------------|----------------------|
| Density | 1130 | kg/m ³ | ISO 1183 |
| Moisture Content | 0.1 | % | - |

| Material specific properties | Value | Unit | Test Standard |
|-------------------------------------|--------------|--------------------|----------------------|
| ISO Data | | | |
| Viscosity number | 135 | cm ³ /g | ISO 307, 1157, 1628 |

Characteristics**Delivery form**

Pellets

Regional Availability

Europe