

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2800	MPa	ISO 527
Yield stress	45	MPa	ISO 527
Charpy impact strength, +23°C	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	14	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Vicat softening temperature, B	190	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	1110	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Special Characteristics

High impact or impact modified

#### Regional Availability

Europe