

Mechanical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	3000 / 1250	MPa	ISO 527
Yield stress	85 / 45	MPa	ISO 527
Yield strain	4.5 / 20	%	ISO 527
Nominal strain at break	15 / >50	%	ISO 527
Charpy impact strength, +23°C	N / N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	8 / 60	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	7 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	7 / 60	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength Temperature	5 / -	kJ/m <sup>2</sup>	ISO 180/1A
	-30	°C	-

Thermal properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	175 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	85 / *	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn. Thickness tested	V-2 / *	class	IEC 60695-11-10
Burning behav. at thickness h Thickness tested	V-2 / *	class	IEC 60695-11-10
Glow Wire Flammability Index (GWFI)	0.8 / *	mm	-
Glow Wire Ignition Temperature (GWIT)	960	°C	IEC 60695-2-12
GWFI - thickness tested (1)	1.5	mm	-
GWIT - thickness tested (1)	875	°C	IEC 60695-2-13
	1.5	mm	-

Electrical properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Relative permittivity, 1MHz	3.4 / 7	-	IEC 62631-2-1
Dissipation factor, 1MHz	225 / 3000	E-4	IEC 62631-2-1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E10	Ohm	IEC 62631-3-2
Electric strength	100 / 60	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	9.5 / *	%	Sim. to ISO 62
Humidity absorption	3 / *	%	Sim. to ISO 62
Density	1130 / -	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 4	h	-
Processing humidity	≤0.15	%	-
Melt temperature	250 - 270	°C	-
Mold temperature	40 - 60	°C	-

## Characteristics

### Processing

Injection Molding

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa