

Bergamid™ B70 UF V2

PA6

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	3000	MPa	ISO 527
Yield stress	80	MPa	ISO 527
Yield strain	4	%	ISO 527
Charpy impact strength, +23°C	87	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, -30°C	5	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	170	°C	ISO 75-1/-2
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Volume resistivity	1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	1E10	Ohm	IEC 62631-3-2
Other properties			
Density	1130	kg/m ³	ISO 1183

Characteristics**Processing**

Injection Molding

Delivery form

Pellets

Special Characteristics

Flame retardant

Regional Availability

Europe, Asia Pacific, Near East/Africa