

Bergamid™ B700

PA6

Avient Corporation

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1100	MPa	ISO 527
Yield stress	50	MPa	ISO 527
Yield strain	22	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	65	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	170	°C	ISO 75-1/-2

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	7	-	IEC 62631-2-1
Dissipation factor, 1MHz	300	E-4	IEC 62631-2-1
Volume resistivity	1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	1E10	Ohm	IEC 62631-3-2
Electric strength	60	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

Other properties	Value	Unit	Test Standard
Density	1130	kg/m ³	ISO 1183

Characteristics**Delivery form**

Pellets

Regional Availability

Europe, Asia Pacific, Near East/Africa