

**Chemlon® 212**

PA6

Teknor Apex Co.

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Mold Shrinkage, MD	<b>0.014</b>	mm/mm	ASTM D 955
Mold Shrinkage, TD	<b>0.018</b>	mm/mm	ASTM D 955
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength	<b>79.3</b>	MPa	ASTM D 638
Elongation at Yield	<b>5</b>	%	ASTM D 638
Elongation at Break	<b>50</b>	%	ASTM D 638
Flexural Modulus	<b>2861</b>	MPa	ASTM D 790
Flexural Strength	<b>103</b>	MPa	ASTM D 790
Izod Impact notched, 1/8 in	<b>53.4</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
UL 94 Flame rating	<b>V-2</b>	-	UL 94
Thickness tested	<b>0.813</b>	mm	-
DTUL @ 66 psi	<b>185</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>60</b>	°C	ASTM D 648
Melting Temperature	<b>220</b>	°C	ASTM D 3418
Limiting Oxygen Index	<b>25</b>	%	ASTM D 2863
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Dielectric Strength, Short Time	<b>14</b>	kV/mm	ASTM D 149
Volume Resistivity	<b>1020</b>	Ohm*cm	ASTM D 257
<b>Other properties</b>			
Density	<b>1130</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Additives**

Lubricants

**Regional Availability**

North America, Europe, Asia Pacific

**Applications**

General Purpose