

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
<sup>[C]</sup> Tensile Modulus	<b>10500</b>	MPa	ISO 527
<sup>[C]</sup> Stress at break	<b>47</b>	MPa	ISO 527
<sup>[C]</sup> Strain at break	<b>0.6</b>	%	ISO 527
<sup>[C]</sup> Charpy impact strength, +23°C	<b>4.5</b>	kJ/m <sup>2</sup>	ISO 179/1eU

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
<sup>[C]</sup> Density	<b>1620</b>	kg/m <sup>3</sup>	ISO 1183

[C]: CAMPUS

## Characteristics

### Special Characteristics

Increased electrical conductivity, Thermally Conductive

### Features

EMI Attenuation/Shielding