

Mechanical properties	dry / cond	Unit	Test Standard
ASTM Data			
Tensile Strength	44.8 / 29	MPa	ASTM D 638
Elongation at Break	80 / 150	%	ASTM D 638
Flexural Modulus	1790 / 621	MPa	ASTM D 790
Flexural Strength	61.4 / 27.6	MPa	ASTM D 790
Izod Impact notched, 1/8 in	850 / N	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	135	°C	ASTM D 648
DTUL @ 264 psi	51.7	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1060	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Regional Availability

North America

Additives

Lubricants