

DOMAMID 6

PA6

DOMO Engineering Plastics

Processing/Physical Characteristics	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	1.0 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1 / *	%	ISO 294-4, 2577

Mechanical properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	3200 / 1000	MPa	ISO 527
Yield stress	80 / 40	MPa	ISO 527
Strain at break	40 / >50	%	ISO 527
Flexural modulus, 23°C	2800 / 900	MPa	ISO 178
Charpy impact strength, +23°C	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	4.5 / 20	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	N / N	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	4.5 / 19	kJ/m ²	ISO 180/1A
Rockwell hardness	R 120	-	ISO 2039-2

Thermal properties	dry / cond	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	221 / *	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	65 / *	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	175 / *	°C	ISO 75-1/-2
Vicat softening temperature, B	200 / *	°C	ISO 306
Burning behav. at thickness h	V-2 / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	-

Electrical properties	dry / cond	Unit	Test Standard
ISO Data			
Volume resistivity	1E13 / -	Ohm*m	IEC 62631-3-1
Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
Comparative tracking index	600 / -	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Density	1140 / -	kg/m ³	ISO 1183

Material specific properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	145 / *	cm ³ /g	ISO 307, 1157, 1628

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	75 - 85	°C	-
Pre-drying - Time	2 - 4	h	-
Melt temperature	230 - 250	°C	-
Mold temperature	60 - 90	°C	-

Characteristics**Processing**

Injection Molding

Applications

General Purpose

Regional Availability

North America, Europe, Asia Pacific