

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.017	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength	40	MPa	ASTM D 638
Elongation at Break	40	%	ASTM D 638
Flexural Modulus	1500	MPa	ASTM D 790
Flexural Strength	60	MPa	ASTM D 790
Izod Impact notched, 1/8 in	590	J/m	ASTM D 256

Other properties	Value	Unit	Test Standard
Water Absorption, Equilibrium	1.2	%	ASTM D 570
Density	1100	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets, Black

Additives

Lubricants

Special Characteristics

Heat stabilized or stable to heat

Certifications

Recycled Resin Content

Applications

General Purpose

Regional Availability

North America