

Product Texts

LNP LUBRICOMP WFL36E compound is based on Polybutylene Terephthalate (PBT) resin containing 30% glass fiber and 15% PTFE. Added features of this grade include: Easy Molding and Wear Resistant.

UL Yellow Card Link [E45329-101284059](https://www.ulprospector.com/usa/Products/Plastics/Engineering-Plastics/101284059)

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	10100	MPa	ISO 527
Stress at break	114	MPa	ISO 527
Strain at break	2.5	%	ISO 527
Flexural modulus	9500	MPa	ISO 178
Izod impact strength, +23°C, 4mm	45	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	10	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	207	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	120	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	-

Other properties	Value	Unit	Test Standard
Density	1700	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.05	%	-
Melt temperature	240 - 265	°C	-
Mold temperature	80 - 100	°C	-
Zone 1	220 - 230	°C	-
Zone 2	245 - 255	°C	-
Zone 3	260 - 270	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific